


Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106 1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client : Verosol 2 Garema C Kingsgrove				Test Number : Issue Date : Print Date : Order Number:	18-00687 28/11/20 26/07/20 028882-1	18
Sample Description	Nominal Mass per Unit Area/De	% Polyester	250+/-5%			
6 1530.2-1993	Methods for Fire Tests on Bui Part 2: Test for Flammability o	-	lls, Compone	ents and Structure	S.	
	Date Tested				27/11/2018	
	Flammability Index				1	
				Length	Width	
	Spread Factor			0	0	
	Heat Factor			1	1	
	Maximum height (d)					
	Mean			2.8	2.8	
	Coefficient of Variation			19.1	10.0	%
	Heat (a)					
	Mean			1.6	1.5	°C.min
	Coefficient of Variation			12.9	0.0	%
	Number of Specimens Tested			6	6	
	Observation	Melting and v	isible smoke			

These test results relate only to the behaviour of the test specimens of the material under the particular conditions of the test, and they are not intended to be the sole criterion for assessing the potential fire hazard of the material in use.



MANAGING DIRECTOR