AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

TEST REPORT

Client: Verosol

21 Amour Street

Revesby NSW 2212

Test Number :

21-002509

Issue Date

21/05/2021

Print Date

31/05/2021

Sample Description

"231 - Veroscreen G3" Clients Ref:

Coated woven fabric

Colour: Black

End Use: Internal Window Blinds

Nominal Composition:

30% Polyester, 70% PVC

Nominal Mass per Unit Area/Density:

Approx: 425g/m2

Nominal Thickness:

Approx: 0.63mm

AS/NZS 1530.3-1999

Methods for Fire Tests on Building Materials, Components and Structures

Part 3: Simultaneous Determination of Ignitability, Flame Propagation, Heat Release and Smoke Release

Face tested:

Face

Date tested:

Ignition time

24-10-2019

Mean

Standard Error 0.71

4.68 min

Flame propagation time Nil Heat release integral 2.5

Nil sec 39.0 kJ/m²

Smoke release, log d

Optical density, d

0.0163 -0.2042

0.6279 / metre

No of samples which ignited

8

For Samples which ignited Smoke Release (Log D) - Mean

-0.2042

Smoke Release (Log D) - Standard Error

0.0163

No of samples which did not ignite

For Samples which did not ignite

-0.7337

Smoke Release (Log D) - Mean Smoke Release (Log D) - Standard Error

0.0000

Number of specimens tested:

9

Page 1 of 2

238546

Australian Wool Testing Authority Ltd Copyright - All Rights Reserved

51777

Accredited for compliance with ISO/IEC 17025 - Testing

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

Chris Campbell

HAFL A. JACKSON B.Sc.(Hons)

0204/11/06

APPROVED SIGNATORY

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

TEST REPORT

Client: Verosol

21 Amour Street

Revesby NSW 2212

Test Number :

21-002509

Issue Date

21/05/2021

Print Date : 3

31/05/2021

Regulatory Indices:

Ignitability Index
Spread of Flame Index

Heat Evolved Index
Smoke Developed Index

15 Range 0-20

0 Range 0-101 Range 0-10

7 Range 0-10

These results only apply to the specimen mounted, as described in this report. The result of this fire test may be used to directly assess fire hazard, but it should be recognised that a single test method will not provide a full assessment of fire hazard under all fire conditions.

The reaction of thin unsupported flexible materials to flame impingement can be assessed in accordance with AS 1530.2. Where materials of thickness less than 2mm that are sufficiently flexible to be bent by hand around a mandrel of 2mm diameter or less are subjected to the test described herein, they should also be subjected to the test in AS 1530.2.

Ignition is initiated by a pilot flame that is held near, but does not touch the specimen. A material that does not ignite during the standard test may ignite if contacted with a pilot flame during the test

The specimens were mounted to simulate use in an unsupported or free hanging mode. The results may be significantly different when mounted to simulate a wall cladding or upholstery application.

To allow free movement of sample during testing all corners were folded away from the clamps.

Each test specimen was sandwiched between two layers of galvanised welded square mesh made from wire of nominal diameter 0.8mm and nominal spacing 12mm in both directions, stapled through at four points, each 100mm from the centre of the sample and the assembly clamped in four places.

238546 51777 Page 2 of 2

 Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

Chris Campbell

MICHAEL A. JACKSON B.Sc.(Hons)

APPROVED SIGNATORY